



100 mm THRU 450 mm DIAMETERS = 3750 mm  
 525 mm THRU 900 mm DIAMETERS = 4275 mm  
 300 mm THRU 900 mm DIAMETERS = 6725 mm

NOMINAL DIAMETERS (mm.)	AVERAGE O.D. (SPIGOT) (mm.)	AVERAGE O.D. (BELL) (mm.)	AVERAGE I.D. (mm.)	PIPE STIFFNESS (kPa)	MINIMUM FLATTENING (%)
100	109.2	124	99.1	320	40
150	162.6	175	149.9	320	40
200	218.4	236	200.7	320	40
250	274.3	297	248.9	320	40
300	325.1	353	297.2	320	40
375	398.8	429	363.2	320	40
450	487.7	523	447.0	320	40
525	574.0	625	525.8	320	40
600	650.2	709	596.9	320	40
750	817.9	892	749.3	320	40
900	983.0	1074	901.7	320	40

**SCOPE**

THIS SPECIFICATION INCLUDES MATERIALS, TEST METHODS AND INSTALLATION REQUIREMENTS FOR 100 mm TO 900 mm DIAMETER POLYVINYL CHLORIDE (PVC) CORRUGATED PIPE WITH A SMOOTH INTERIOR. THE REQUIREMENTS OF THIS SPECIFICATION ARE INTENDED TO PROVIDE PIPE AND FITTINGS SUITABLE FOR UNDERGROUND USE IN NON-PRESSURE APPLICATIONS SUCH AS SANITARY SEWERS, STORM SEWERS, DRAINAGE AND UNDERDRAINS.

**PIPE**

PVC CORRUGATED PIPE WITH A SMOOTH INTERIOR SHALL CONFORM TO THE REQUIREMENTS OF ASTM DESIGNATION F949. PIPE AND FITTINGS SHALL BE HOMOGENEOUS THROUGHOUT AND FREE FROM VISIBLE CRACKS, HOLES, FOREIGN INCLUSIONS OR OTHER INJURIOUS DEFECTS. PIPE SHALL BE MANUFACTURED TO 320 kPa STIFFNESS WHEN TESTED IN ACCORDANCE WITH ASTM TEST METHOD D2412. THERE SHALL BE NO EVIDENCE OF SPLITTING, CRACKING OR BREAKING WHEN THE PIPE IS TESTED PER ASTM TEST METHOD D2412 IN ACCORDANCE WITH ASTM F949 SECTION 7.5 AND ASTM F794 SECTION 8.5. THE PIPE SHALL BE MADE OF PVC COMPOUND HAVING A MINIMUM CELL CLASSIFICATION OF 12454 AS DEFINED IN ASTM SPECIFICATION D1784.

**FITTINGS:**

ALL FITTINGS FOR PVC CORRUGATED SEWER PIPE WITH A SMOOTH INTERIOR SHALL CONFORM TO ASTM F949, SECTION 5.2.3 OR F794, SECTION 7.2.4. TO INSURE COMPATIBILITY, THE PIPE MANUFACTURER SHALL PROVIDE ALL FITTINGS.

**JOINTS:**

ALL JOINTS SHALL BE MADE WITH INTEGRALLY-FORMED BELL AND SPIGOT GASKETED CONNECTIONS. THE MANUFACTURER SHALL PROVIDE DOCUMENTATION SHOWING NO LEAKAGE WHEN GASKETED PIPE JOINTS ARE TESTED IN ACCORDANCE WITH ASTM TEST METHOD D3212. ELASTOMERIC SEALS (GASKETS) SHALL MEET THE REQUIREMENTS OF ASTM DESIGNATION F477.

CONTECH ID# 0000



9025 CENTRE POINTE DRIVE, SUITE 400  
 WEST CHESTER, OHIO 45069  
 PH: 1.800.338.1122 FAX: 513.645.7399

THIS PRINT IS OWNED BY CONTECH CONSTRUCTION PRODUCTS INC. AND MUST BE RETURNED UPON REQUEST. NOT TO BE COPIED.

© COPYRIGHT

**A-2000 PVC SEWER PIPE**

PRODUCT SPECIFICATION  
 FOR (F949) PVC PIPE  
 (METRIC)

SCALE: N/A

DRAWN BY: FAM  
 DATE: 10/10/08

REV. BY: —

DATE: —

SHEET:

1 of 1

H:\DRAINAGE SOLUTIONS\ACAD DATA\DRAINAGE DETAILS\A-2000.dwg A-2000 SEWER PIPE mm (10-10-08 FAM).dwg 10/21/2008 2:25:53 PM EDT