

SPECIFICATION

BLACK METRIC SHEET PILING

- Scope:** This specification covers structural quality, light gage, interlocking steel sheet piling.
- Material:** Black steel shall conform to the requirements of ASTM A 1011 (Grade 30). The minimum yield point shall be 30,000 psi and the minimum tensile strength shall be 49,000 psi.
- Manufacture:** The sheet piling shall be manufactured in accordance with ASTM A 857, "Standard Specification for Steel Sheet Piling, Cold Formed, Light Gage".
- Product:** The nominal physical properties of the steel sheet piling shall conform to the requirements tabulated below.

GAGE	THICKNESS (in.)	SECTION MODULUS (in ³)	
		PER SECTION	PER FT.
12	0.1046	3.18	1.76
10	0.1345	4.07	2.25
8	0.1644	4.95	2.75
7	0.1793	5.39	2.99
5	0.2092	6.28	3.48

- Additional Requirements:** The sides of each piece of sheet piling shall be furnished with an interlock that is continuous for the full length of the sheeting.
- Certifications:** Upon request, the manufacturer shall certify that the requirements of this specification have been met.
- Reference:** Reference the project plans for the gage, length, special sections and quantity requirements.



© COPYRIGHT

SPECIFICATION
BLACK
METRIC SHEET PILING

DRAWN BY: JME	REV. BY: M.J.O.	SCALE:
DATE: 9-18-92	DATE: 4-15-03	SCALE: 1008808E